# GLAZE LAYERING

## CYAN SCALES



VITRAGIAZE STONEWARE GLAZE: SAFFRON

Clay used:Vitraclay Studio Throwing



# VITRAGIAZE STONEWARE

GLAZE: CELADON

Firing: Layered pot fired to 1250°C

## BLUE PATINA



VITRAGIAZE STONEWARE GLAZE: RUSTY MOTTLE



VITRAGLAZE STONEWARE GLAZE: ISLAND TURQUOISE

Firing: Layered pot fired to 1250°C

## OCEAN BREAK





Clay used: Vitraclay Studio Throwing



#### VITRAGIAZE STONEWARE GLAZE: TIN WHITE SPECKLE

t this dry (5 - 10 mins) then add 2 layers of your second glaze

iring: Layered pot fired to 1250°C

#### HONEY POT



VITRAGLAZE STONEWARE GLAZE: TIN WHITE SPECKLE



VITRAGIAZE STONEWARE GLAZE: LIQUORICE BLACK

Let this dry (5 - 10 mins) then add

#### **VOLCANIC ASH**



VITRAGLAZE STONEWARE GLAZE: RUSTY MOTTLE

Start by adding 2 generou layers of your first glaze



VITRAGLAZE STONEWARE GLAZE: REACTIVE WHITE

Let this dry (5 - 10 mins) then add

#### COKE



VITRAGLAZE STONEWARE GLAZE: SAFFRON

Start by adding 2 generou layers of your first glaze



VITRAGLAZE STONEWARE GLAZE: LIQUORICE BLACK

this dry (5 - 10 mins) then add lavers of your second glaze

#### GREEN METAL



VITRAGLAZE STONEWARE GLAZE: REACTIVE WHITE

Start by adding 2 generous layers of your first glaze



VITRAGLAZE STONEWARE GLAZE: METALLIC PATINA

# STARRY NIGHT



VITRAGIAZE STONIEWARE GLAZE: REACTIVE WHITE

Start by adding 2 generou layers of your first glaze



VITRAGIAZE STONIEWARE GLAZE: DENIM BLUE

Let this dry (5 - 10 mins) then add 2 layers of your second glaze

Firing: Layered pot fired to 1250°C

# CARIBBEAN SEA



GLAZE: REACTIVE WHITE

Start by adding 2 generol layers of your first glaze



VTTRAGIAZE STONEWARE GLAZE: ISLAND TUROUOTSE

Let this dry (5 - 10 mins) then add 2 layers of your second glaze

## MIDNIGHT SNOW



VITRAGLAZE STONEWARE GLAZE: TIN WHITE SPECKLE



VITRAGLAZE STONEWARE GLAZE: OXIDE GREEN

Firing: Layered pot fired to 1250°C

# SEAWEED GREEN



GLAZE: SAFFRON

Clay used:Vitraclay Studio Throwing

VITRAGLAZE STONEWARE







iring: Layered pol fired to 1250°C



#### VITRAGLAZE STONEWARE VITRAGLAZE STONEWARE GLAZE: OXIDE GREEN GLAZE: REACTIVE WHITE



CAPPUCCINO





Firing: Layered pot fired to 1250°C